

Evidence of performance
Airborne sound insulation of building components


Test Report

No. GLA-1295.1/16 E

Client**Pilkington IGP Sp. z o.o.**

ul. Portowa 24

27-600 Sandomierz

Product:	Insulating glass unit
Construction:	44.2 / 18 / 4 / 16 / 6
Designation:	Optilam 8,8 mm 44.2 / 18 Ar / Optifloat 4 mm / 16 Ar / Optifloat 6 mm
Dimension:	1230mm x 1480mm
Gas filing:	Argon
Area related mass	48 kg/m ²
Cross-section:	
Rating	Weighted sound reduction index R_w and the spectrum adaptation terms: C and C_{tr}
Basis	EN ISO 10140-1:2010 EN ISO 10140-2:2010 EN ISO 717-1: 2013
Value	$R_w (C; C_{tr}) = 41 (-1; -6) \text{ dB}$

Łozienica, 14.02.2017


PhD Krzysztof Mech
Head of Acoustics Laboratory