

Evidence of performance
Airborne sound insulation of building components


Test Report

No. GLA-1295.9/16

Client**Pilkington IGP Sp. z o.o.**

ul. Portowa 24

27-600 Sandomierz

Product:	Insulating glass unit
Construction:	10 / 24 / 4
Designation:	Optifloat 10 mm / 24 Ar /Optifloat 4mm
Dimension:	1230 mm x 1480 mm
Gas filing:	Argon
Area related mass	36 kg/m ²
Cross-section:	
Rating	Weighted sound reduction index R_w and the spectrum adaptation terms: C and C_{tr}
Basis	EN ISO 10140-1:2010 EN ISO 10140-2:2010 EN ISO 717-1: 2013
Value	$R_w (C; C_{tr}) = 39 (-3; -7) \text{ dB}$

Łozienica, 10.01.2017

**PhD Krzysztof Mech**
Head of Acoustics Laboratory