



Technical Bulletin

ATS-135
04/2025

PILKINGTON ENERGY ADVANTAGE™ GUIDELINES

Summary

Pilkington **Energy Advantage™** Low-E glass is a hard, neutral color; pyrolytic coating on clear glass, which gives, improved thermal insulation (U-Factor) to glazed windows. The coating is tough and durable, and for most situations the product can be treated in the same way as uncoated glass.

Unpacking

The coated surface is hard and is not easily damaged, so cases can be opened normally.

Do not mark the coated surface with adhesive labels or wax crayons, and do not drag suction cups or metal objects across the surface. The coating will not be damaged by such materials, but it may be difficult to remove deposited fine rubber or metal residues due to the submicroscopic roughness of the coating.

Surface Identification

The coating is electrically conductive so a hand-held ohm-meter or continuity checker can be used to identify the coated side by touching the two probes to the coating.

Note: While the two probes of the ohm-meter can indicate the electrical continuity of a low-e coating they cannot accurately measure the Ohm/Square conductance of the coating. For that

Pilkington North America, Inc.

811 Madison Avenue, Toledo, Ohio 43604-5684

Telephone 800 221 0444 Fax 419 247 451

measurement a 4-point probe contact meter is needed. Take care not to drag probes across the coating surface because they could deposit a metal mark.

Handheld meters to identify the presence of the coating on the inaccessible surfaces within an insulated glazing unit, and 4-point probe meters are available from EDTM at <https://www.edtm.com>.

With practice the coating can be felt by the increased drag on fingertips or a fingernail when rubbed on the coated side. Additionally, an ordinary lead pencil will lightly write on the coating but not on the glass surface. These techniques should be used near the edge of the glass where it will be within a frame when glazed.

Inspection

Inspections should be performed in accordance with ASTM C1036 and C1376 as best practice. Glass should be inspected in transmission, unless otherwise noted, by viewing through the glass to a uniformly bright surface 1700 lux – 2500 lux (160 fc - 230 fc) with a dark background behind the viewer (to eliminate distracting reflections) to simulate daytime viewing of the glass from within a building.

The glass can be inspected, in reflection, for uniformity of coating by placing it in front of a matte black non-reflective background with a uniformly lit white surface, behind the viewer, reflected onto the glass. This simulates the viewing condition where a person outside looks at the daytime reflection of an overcast sky.

Fabrication

Cutting

The glass can be cut with the coating side up or down depending on preference, but coating side up is recommended to minimize the risk of marking the coating. Cutting wheel pressures will be very similar to those for uncoated glass.

When hand cutting on the coated surface the score may feel slightly different but no change in wheel types is needed from those used with uncoated glass of the same thickness.

If the glass is to be dragged across rollers or over a poorly inflated air-float table it is preferable to have the coating side up to avoid rub marks. However, care must be taken if straight edges, metal tape measures, or cutting bars are dragged on the coated top surface, as marking may occur which would require special cleaning techniques.

Edge preparation such as seaming or polishing should be done coated side up, as the rotation of the seaming table casters could cause a swirling pattern where the caster would touch the coating if it were facing down.

Pilkington North America, Inc.

811 Madison Avenue, Toledo, Ohio 43604-5684

Telephone 800 221 0444 Fax 419 247 4517

Washing

Automatic washing machines using hot water and detergents, such as Alconox, can be used, as with uncoated glass.

Razor blades and steel wool must not be used on the Low-E coated surface.

Abrasive cleaners should only be used with great caution as they can often create relatively light or dark areas which are only visible under certain lighting conditions.

Heat Treating

As with all Low-E glasses, the coating will reflect radiant heat and so it will require a longer furnace cycle to achieve the same uniform temperature as uncoated glass of the same thickness. Note that with the coated side facing up, the bottom surface will run hotter and will need to be watched for roller marking or center-rub ("Skunk Stripe") from temporary warping or overheating.

For Pilkington **Energy Advantage™** with the coating up, the furnace cycle time can be 20% or more, greater than that for non-coated glass of the same thickness.

A very rough rule of thumb for heating non-coated, clear glass for tempering is: 1 second in the furnace for each 0.001 inch of thickness. i.e. 6 mm (0.222") glass will require about 3 ½ minutes heating time. Individual furnace times will differ.

With the coating down, a more rapid heating may be achieved by thermal convection and conduction to the lower surface, and radiation heating to the top surface. However, care must be taken to prevent any sliding actions which could cause marking from the furnace rolls, or from the loading and unloading conveyors.

The forced convection heat loss during the quench is little affected by the presence of the Low-E coating but normal air flow adjustments may be required to prevent bowing and obtain an acceptable break pattern if the glass is not at the exact same temperature as uncoated glass of the same thickness.

Insulating Glass

In insulating glass configurations with only one low-e coating present, the coated surface will face the air space. Note: the winter U-Factor is unchanged with the coating on either the number 2 or number 3 surface. The coating should be on the number 3 surface to maximize the passive solar gain in winter. When the coating is on the number 2 surface there is a lower solar heat gain coefficient and less passive solar gain.

It is important to confirm that the glass is effectively cleaned, and that full sealant adhesion is developed to the coated surface. It is the IG manufacturer's responsibility to ensure that sealant adhesion is satisfactory. To date, Pilkington **Energy Advantage™** Low-E has been

Pilkington North America, Inc.

811 Madison Avenue, Toledo, Ohio 43604-5684

Telephone 800 221 0444 Fax 419 247 4517

tested, and found compatible, for IG construction, without edge deletion, with Hot Melt Butyls, Polyisobutylenes, Polysulphides, Urethanes and One- and Two-Part Silicones.

Do not allow aluminum spacers to drag across the coated surface when assembling the units or a metal deposit will be left on the coating.

Laminating

Laminated glass must be fabricated with the coating out, away from the PVB interlayer, to preserve the Low-E effect.

A laminate can physically be made with the Low-E coating placed against the PVB interlayer, but the low emissivity property will be lost. If the laminate is made with the coating against the PVB there will be a slight reduction of SHGC, compared to clear, non-coated glass, caused by absorption of some solar near-IR radiation. (Optics and Window 5 programs can compute this for Pilkington NA Inc. Low-E coatings). For optimal SHGC and U-factor benefits, Pilkington **Energy Advantage™** should be placed on the interior exposed surface (#4) of a monolithic laminated configuration.

The Pilkington **Energy Advantage™** Low-E coating is not damaged by normal laminating processes. Care should be taken to minimize excess PVB remaining around the edge of the glass prior to autoclaving, as this can be difficult to remove from the coated surface. Do not use razor blades or steel wool to remove deposits from the coated surface.

Impact testing should be repeated to ensure the safety fracture properties of laminated glass have been preserved.

Packing

When packing Pilkington **Energy Advantage™** Low-E coated glass for shipping with the coating exposed, it is preferable to use paper or hardwood flour as an interleaving medium. Over long distances, the acrylic beads in Lucor powder can be abraded and leave a deposit on the coating which is difficult to remove.

Care should also be taken to minimize the contact of Styrofoam packing materials with the coated surface. Styrofoam packing materials can leave a rub mark on the coating that is difficult to remove.

Pilkington North America, Inc.

811 Madison Avenue, Toledo, Ohio 43604-5684

Telephone 800 221 0444 Fax 419 247 4517

Change Summary	Date
Format Update; include inspection lighting conditions; modify lamination section	04/29/2025

The information contained in this bulletin is offered for assistance in the application of Pilkington North America Inc. flat glass products, but **IT DOES NOT CONSTITUTE A WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE.** Actual performance may vary in particular applications.

Pilkington North America, Inc.

811 Madison Avenue, Toledo, Ohio 43604-5684

Telephone 800 221 0444 Fax 419 247 4517